



# Elsanek Ref. Olefine 150

**UNIFORMTECH**
**olefine**  
TECHNOLOGY

Azul/Blue 2727CP

Verde/Green 7726CP

Azul/Blue 2717CP

Gris/Grey 429CP

Blanco/White


**Composición / Composition**
**99% Olefine + 1% Antistatic**

Peso / <i>Weight</i> (gr/m <sup>2</sup> )	<b>150 ± 5</b>		UNE 40-339-76
Ligamento / <i>Ligament</i>	Sarga 2E1		
Ancho / <i>Width</i> (cm)	<b>160 ± 1</b>		
Resistencia a la tracción / <i>Tensile strength</i> (kg)	Urdimb / <i>Warp</i> <b>90 ± 5%</b> Trama / <i>Weft</i> <b>85 ± 5%</b>		UNE EN13934-1
Resistencia al rasgado / <i>Tear strength</i> (kg)	Urdimb / <i>Warp</i> <b>5.5 ± 5%</b> Trama / <i>Weft</i> <b>5.5 ± 5%</b>		UNE EN13937-2
Encogimiento al lavado 75°C / <i>Washing shrinkage 75°C</i>	<b>2%</b>		EN 6330/15797
Eficacia de la filtración bacteriana (BFE %) / <i>Bacterial Filtration Efficiency (BFE %)</i>	<b>93.38% ± 4.81%</b> <b>(1)</b>	<b>82% ± 3%</b> <b>(2)</b>	EN14683:2019 + AC2019 (*)
Respirabilidad: Presión diferencial (Pa/cm <sup>2</sup> ) / <i>Breathability: Differential pressure (Pa/cm<sup>2</sup>)</i>	<b>32.6 ± 1</b> <b>(1)</b>	<b>21.6 ± 1</b> <b>(2)</b>	EN14683:2019 + AC2019 (*)
Anti estático / <i>Antistatic</i>	<b>Pass</b>		EN1149/3
Antiácido / <i>Antiacid</i>	<b>Clase 3 / Clase 2</b>		EN13034 (Ácido Sulfúrico/ Hidróxido Sódico)

**PROPIEDADES INHERENTES / INHERENT PROPERTIES**

 (\*) Test realizado sobre mascarilla / *Test made by mask*

 Reciclable / *Recyclable*

 Imprescindible fornituras termoplásticas de baja temperatura de fusión (190-200<sup>o</sup>) en prenda. / *Essential thermoplastic fittings of low melting temperature (190-200<sup>o</sup>) in garment.*
**(1) UNE 0065:2020** 0-5 lavados/washes / **(2) CWA17553:2020** después de 50 lavados/after 50 washes

**Instrucciones de lavado / Washing instructions:**

 Temperatura lavado:  
recomendado a 40°C / max. 75°C  
*Washing temperature:  
recommended at 40°C / max. 75°C*

 Permite el uso de lejía, cloro o cualquier otro detergente.  
*It allows the usage of bleach, chlorine or any other detergent*

**Secado con secadora:** Temperatura recomendada:  
40°C (max. 40°C). Duración: máximo 20 minutos +  
5 minutos en frío (en función de la carga). /  
**Secado con tunel de secado:** Temperatura  
recomendada: 70°C (max. 70°C).

**Drying using a drying machine:** *Recommended temperature: 40°C (max. 40°C). Duration: maximum 20 minutes + 5 minutes cold wash (depending on the load).* / **Drying using tunnel:** *Recommended temperature: 70°C (max. 70°C).*

 No planchar  
*Do not iron*

 Se recomienda plegar o colgar la pieza de ropa después del proceso de secado para reducir las arrugas.  
*It is recommend to fold or hang the garments after finishing the drying process in order to reduce the amount of wrinkles.*