



Elsaneek Ref. **SpitProtect 400**

QUIROTECH

[SpitProtect]
TECHNOLOGY

Composición / <i>Composition</i>	99,5% PE 0,5% Antistatic	
Peso / <i>Weight</i> (gr/m)	400 ± 5%	UNE 40-339-76
Ligamento / <i>Ligament</i>	1E1	
Ancho / <i>Width</i> (cm)	145 ± 1	
Encogimiento al lavado 75°C / <i>Washing shrinkage 75°C</i>	1%	EN 6330/15797
Resistencia a la tracción / <i>Tensile strength</i> (kg)	Urdimb / <i>Warp</i> 180± 5% Trama / <i>Weft</i> 100± 5%	UNE 40-085
Resistencia al desgarre / <i>Tear strength</i>	Urdimb / <i>Warp</i> 3,5± 5% Trama / <i>Weft</i> 3,0± 5%	UNE 40-085
Antiestático / <i>Antistatic</i>	Pass	EN 1149-1
Normativa europea Quirofano / <i>Surgical European regulation</i>	Pass	EN 13795
Resistencia Térmica / <i>Thermal resistance</i>	0,2122 Rct (m² K/L)	EN 11092:2014

Instrucciones de lavado / *Washing instructions:*



Lavar a 40°C - 60°C
Wash at 40°C - 60°C



No permite el uso de lejía
Bleach NOT allowed



Secadora: 60-80°C Max: 15-25 min (según carga)
Tumble: 60°-80°C Max: 15-25 minutes (depending on the load)



No planchar
Do not iron